

AIR MAIL

18980.0

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US).
CONCERNING A FILING UNDER 35 U.S.C. 371**

U.S. APPLICATION NO

10/018465

INTERNATIONAL APPLICATION NO.
PCT/EP00/06688


INTERNATIONAL FILING DATE
July 13, 2000

PRIORITY DATE CLAIMED
July 13, 1999

TITLE OF INVENTION: BRISTLE, METHOD FOR PRODUCING A BRISTLE AND BRUSHWARE
COMPRISING SUCH BRISTLES

APPLICANT(S) FOR DO/EO/US

WEIHRAUCH, Georg



Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a FIRST submission of items concerning a filing under 35 U.S.C. 371
2. ☐ This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(I)
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C.371(c)(2)).
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US)
6. ☒ A translation of the International Application into English (35 U.S.C.371(c)(2)).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C.371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau)
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C.371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C.371(c)(4)).
10. ☒ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C.371(c)(5)).

Items 11. to 16. below concern document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A FIRST preliminary amendment.
☐ A SECOND or SUBSEQUENT preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☒ Other items or information:
 1. Form PCT/IB/308
 2. Return Postcard
 3. Conditional Petition to Revive

U.S. APPLICATION NO	INTERNATIONAL APPLICATION NO PCT/EP00/06688	531 Rec'd 10/018465 ATTORNEYS DOCKET NO. 18980 0 10 DEC 2001
17. The following fees are submitted:		CALCULATIONS PTO USC Only
BASIC NATIONAL FEE (37 CFR 1.492 (a) (1)-(5)): Search Report has been prepared by the EPO or JPO.. \$ 890.00 International preliminary examination fee paid to USPTO\$710.00 No international preliminary examination fee paid to USPTO but international search fee paid to USPTO.....\$740.00 Neither international preliminary examination fee nor international search fee paid to USPTO.....\$1040 00 International preliminary examination fee paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4).....\$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =		\$ 890
Surcharge of \$130.00 for furnishing the oath or declaration later than <u>20</u> <u>30</u> months from the earliest claimed priority date (37 CFR 1.492(e))		\$
CLAIMS	NUMBER FILED	NUMBER EXTRA
Rate		
Total claims	33 - 20 =	13
		X \$ 18 00
		\$ 234
Independent claims	1 - 3 =	0
		X \$ 84 00
		\$
MULTIPLE DEPENDENT CLAIM(S) (if applicable)		+ \$ 280
		\$
TOTAL OF ABOVE CALCULATIONS =		\$ 1124
Reduction by 1/2 for filing by small entity, if applicable		
SUBTOTAL =		\$ 1124
Processing fee of \$130.00 for furnishing the English translation later than <u>20</u> <u>30</u> months from the earliest claimed priority date + 130		
TOTAL NATIONAL FEE =		\$ 1124
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3 28, 3 31). \$40.00 per property		\$ 40
TOTAL FEES ENCLOSED =		\$ 1164
		Amount to be: refunded \$ charged \$
a. <u> </u> A check in the amount of \$ <u> </u> to cover the above fees is enclosed.		
b. <u>X</u> Please charge my Deposit Account No. <u>50-0698</u> in the amount of \$ <u>1164</u> to cover the above fees.		
c. <u>X</u> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>50-0698</u> . A duplicate copy of this sheet is enclosed.		
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.		
Please send all correspondence by <u>AIRMAIL</u> to:		
Dr. Paul J. Vincent Lichti, Lempert & Lasch Bergwaldstr. 1 D-76227 Karlsruhe Fed. Rep. of Germany		<u>Paul Vincent</u> SIGNATURE Dr. Paul J. Vincent NAME <u>37,461</u> REGISTRATION NUMBER

10/018465

531 Rec'd PCT/TT 19 DEC 2001

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: WEIHRAUCH, Georg) Examiner:
PCT Application No.: PCT/EP00/06688) unknown
PCT Filing Date: July 13, 2000) Art Unit:
For: BRISTLE, METHOD FOR) unknown
PRODUCING A BRISTLE AND)
BRUSHWARE COMPRISING SUCH)
BRISTLES)

Docket No.: 18980.0

Assistant Commissioner for Patents

Washington, DC 20231

U.S.A.

PRELIMINARY AMENDMENT

Dear Sir:

Please enter this amendment prior to calculation of the filing fees. This amendment is based on the translation of the application as amended on August 3, 2001.

IN THE SPECIFICATION:

On page 1, insert as a title prior to the first paragraph --

BACKGROUND OF THE INVENTION --.

On page 5, insert as a title prior to the third paragraph --

SUMMARY OF THE INVENTION --.

On page 12 insert as a title prior to the brief description of the drawings --

BRIEF DESCRIPTION OF THE DRAWING --.

Replace the Brief Description of the Drawings as follows --

Fig. 1a shows a schematic representation of a first typical fissure shape;

Fig. 1b shows a schematic representation of a second typical fissure shape;

Fig. 1c shows a schematic representation of a third typical fissure shape;

Fig. 1d shows a schematic representation of a fourth typical fissure shape;

Fig. 2 shows a measurement diagram of an ampoule-shaped fissure in accordance with the statistical average;

Fig. 3 shows a measurement diagram of the other three fissure shapes in accordance with the statistical average;

Fig. 4a shows a schematic representation of an embodiment of three component bristle;

Fig. 4b shows a representation of the effects of the embodiment of Fig. 4a;

Fig. 5a shows another embodiment of the bristle;

Fig. 5b shows the effects of the bristle of Fig. 5a;

Fig. 6a shows another embodiment of the bristle;

Fig. 6b shows the effects of the bristle of Fig. 6a;

Fig. 7a shows an embodiment of a two component bristle;

Fig. 7b shows the effects of the bristle of Fig. 7a;

Fig. 8a shows another embodiment of a two component bristle;

Fig. 8b shows the effects of the bristle of Fig. 8a;

Fig. 9 shows a schematic illustration of the method for conifying the bristle;

Fig. 10 shows an embodiment of a three-component bristle in an enlarged section;

Fig. 11 shows a further embodiment of a two-component bristle in an enlarged partial view; and

Fig. 12 shows an embodiment of a two-component bristle with a core of monofilaments. --.

On page 13 insert as a title following the brief description of the drawing --

DESCRIPTION OF THE PREFERRED EMBODIMENT --.

On page 19, line 1, replace as a title "Claims" with --
I CLAIM: --.

IN THE CLAIMS:

Please delete **PCT amended claims 1 - 33** without prejudice and enter new claims 34 - 66 as indicated below:

34. A bristle for brushware or brushes, the bristle produced by cutting an extruded monofilament to length, the

bristle comprising:

a core of hard flexible plastic material;
a shaft surrounding said core, said shaft made from a soft elastic plastic material; and
a jacket surrounding said shaft, said jacket made from a material which reinforces said shaft, wherein said core projects past said shaft at a use end of the bristle to give the bristle a tapered, pointed tip.

35. The bristle of claim 34, wherein said shaft consists essentially of a rubber-elastic plastic material.
36. The bristle of claim 34, wherein said shaft consists essentially of an elastomer.
37. The bristle of claim 34, wherein at least one of said shaft and said jacket extend conically towards a tip of said core.
38. The bristle of claim 34, wherein said core has a conical tip.
39. The bristle of claim 34, wherein said core and said shaft can be axially displaced relative to one another.

40. The bristle of claim 34, wherein said shaft and said jacket can be axially displaced relative to one another.
41. The bristle of claim 34, wherein said core is rounded at its tip.
42. The bristle of claim 34, wherein said core is made from one of a thermoplastic material, polyamide, and polyester and said shaft consist essentially of a thermoplastic elastomer.
43. The bristle of claim 34, wherein said jacket consists essentially of one of a thermoplastic material, polyamide, and polyester.
44. The bristle of claim 42, wherein said thermoplastic material is one of polyamide, polyethylene, polypropylene, and polyester.
45. The bristle of claim 34, wherein the bristle extends conically along a partial length of up to 2mm.
46. The bristle of claim 34, wherein the bristle extends conically along a partial length of between 0.1 and 1mm.
47. The bristle of claim 34, wherein a diameter of said core at said pointed tip is between 0.01 and 0.03mm.

48. The bristle of claim 34, wherein said core can be split at least once in a region of its exposed end and can be spread beginning at said exposed end.
49. The bristle of claim 34, wherein said core is split at least once proximate its exposed end at locations spaced apart from said exposed end, wherein said split locations bulge elastically when pressure is exerted on said exposed end.
50. The bristle of claim 34, wherein said core consists essentially of at least two thin monofilaments.
51. The bristle of claim 34, wherein a cross-section of a material structure of the bristle changes from inside to outside.
52. The bristle of claim 34, wherein said core has a material structure of high elasticity and abrasion resistance and said jacket has high bending strength.
53. The bristle of claim 34, wherein the bristle is produced through co-extrusion of at least two of said shaft, said core, and said jacket.

54. The bristle of claim 34, wherein the bristle is produced through extrusion of said jacket onto said co-extruded shaft and core.
55. The bristle of claim 34, further comprising abrasive means embedded in at least a region of said soft shaft.
56. The bristle of claim 34, wherein at least said shaft and said core have different colors.
57. Method for producing the bristle of claim 34, wherein one of the bristle, the monofilament, and a section of the monofilament is conified through grinding by clamping it at a separation from its free end, wherein said core is supported on a circulating grinding surface and set at an inclination with respect to that circulating grinding surface corresponding substantially to a cone angle.
58. The method of claim 57, wherein the bristle, including said core and jacket, is supported on said grinding surface.
59. A method for producing the bristle of claim 34, wherein said core and said shaft are axially displaced relative to one another until part of a length of said core projects past said shaft.

60. A method for producing the bristle of claim 34, wherein said jacket and said shaft are axially displaced relative to one another until a cylindrical partial length of said shaft projects past said jacket.
61. The method of claim 57, wherein at least one of said core, said shaft, and said jacket are stepped, wherein part of a length of at least one of said shaft and said jacket is conical.
62. A brush, comprising a bristle support and a bristle stock mounted thereto, the bristle stock comprising individual bristles or bristles combined into bundles or groups, wherein said bristle stock at least partially comprises the bristles of claim 34.
63. The brush of claim 62, wherein the bristles according to claim 34 are disposed only in defined regions of said bristle stock.
64. The brush of claim 62, wherein said brush is one of a toothbrush and a driven tooth brush.
65. The brush of claim 64, wherein the bristles according to claim 34 are only disposed in defined regions of said bristle stock.

66. The brush of claim 62, wherein said bristles according to claim 34, project past other bristles in said bristle stock.

REMARKS

The amendments have been taken to adapt this application to United States practice. No new matter has been added.

Lichti, Lempert and Lasch
Bergwaldstr. 1
D-76227 Karlsruhe, Germany
Telephone: +49-721-9432815
Fax: +49-721-9432840
-9432850

Paul Vincent

Dr. Paul Vincent
Agent for the Applicant
Registration No. 37,461

10/018465

531 Rec'd PCT... 19 DEC 2001

18980.0

ART 34 AMDT

Translation of PCT/EP00/06688 as amended on August 3, 2001

Bristle, Method for Producing a Bristle and Brushware
Comprising such Bristles

The invention concerns a bristle for brushware or brushes, which is produced by cutting an extruded monofilament to length, and which tapers towards its useful end in a point-like manner, which is made from at least two co-extruded plastic components and has a shaft made from a soft elastic plastic and a core made from a flexible plastic which is harder than that of the shaft, wherein the core projects past the jacket at the use sided end to form a pointed tip. The invention also concerns a method for the manufacture of such bristles and a brush having such bristles.

The effectivity of a tooth brush for cleaning teeth and for tooth care depends mainly on the structure and function of the bristles in addition to the duration of the cleaning time. In the development of tooth brushes, the bristle material, bristle geometry, and the combination of the bristles within the bristle stock are therefore very important. The bristle stock or the bristles forming same must fulfil several functions in tooth care. They must reach the spherical lateral surfaces on the inner and outer sides of the teeth having largely varying curvatures and the useful end of the bristle and/or bristle jacket must work

sufficiently effectively. Moreover, at least individual bristles of the bristle stock should penetrate into the interdental spaces from the inner and outer side of the teeth and the bristles should also exert a massaging action on the gum and, in particular, on the gum edges. Cleaning of the teeth and of the interdental spaces should, in conjunction with the dentifrice used, not only prevent plaque build-up but also remove existing plaque to prevent caries.

Dental tests have shown that in countries where caries prophylaxis is practiced, caries is rarely found on free and substantially flat tooth surfaces because these surfaces are easy to reach and clean with conventional dental hygiene means, such as tooth cleaning means, i.e. tooth brushes, dental floss etc.. Moreover, prophylactic dentifrices which contain e.g. fluorides, can easily reach and treat these surfaces.

Recent studies have shown that approximately 80% of caries originates in the so-called dental fissures most of which are located on the chewing surfaces of the molars and premolars, which are therefore more prone to caries and to larger cavities. These gap-like fissures of very narrow cross-sections are, in and of themselves, an ecosystem which are difficult or impossible to reach with conventional tooth brushes and which foster undisturbed development of caries-generating plaque. Nor do dentifrices reach these locations to a sufficient degree. Additionally, the enamel at the

bottom of the fissures is very thin and contains few minerals which even enhances caries formation at these locations.

Modern dental medicine classifies such fissures according to their geometrical shape into U- V- and I-shaped fissures. These represent approximately 93% of the fissures examined. So-called ampoule-shaped fissures have a considerably reduced occurrence of approximately 7%. These fissures narrow like a funnel to a narrowest location and then widen again like a sack. Additionally, all fissures are curved in their longitudinal extension and the funnel axis is often tilted or curved. Cleaning of these fissures would require extremely thin bristles which would deflect under the smallest loads due to their insufficient bending strength. Fine thin bristles or bristles having finely drawn ends are also desired in other fields, e.g. cosmetic brushes or brushware.

DE 90 12 603 U proposes conification of the bristle ends and at least partially providing the bristle stock of a tooth brush with such bristles to be able to also reach, in particular, the interdental spaces and highly rugged surface structures. The same purpose is fulfilled by a two component bristle (GB 2 325 401 A) having the pre-characterizing features of claim 1. It is made from a shaft of soft elastic plastic e.g. nylon and a core which is harder than the shaft e.g. polyester, so that the conically tapered tip is substantially formed by the harder core. Another two component bristle (WO97/25 902A) has a core made from a plurality of monofilaments projecting past a closed jacket.

No concically tapered tip is envisioned nor would one be possible.

In a known tooth brush having a similar bristle design (EP 0 596 633), the main task is to achieve an improved flexibility in the region of the bristle ends with densely packed bristles and corresponding stability of the bundle, in order to, in particular, guarantee cleaning in the region of the gingival border without injuring the gingiva. Moreover, bristles are known (WO99/24649) which are separated at their ends into flags thereby mainly producing intensification of the bristle action due to multiplication of the bristle ends and action of the individual bristles over a larger surface region due to the flags.

Bristle tips have also been conventionally shaped by inserting them into a solvent - as in dip varnishing - and slowly removing them thereby dissolving the plastic material of the bristle. The bristle end remains in the solvent bath for the longest period of time to thereby form bristles with pointed ends. The method is expensive, environmentally harmful, and the formation of the tip cannot be exactly controlled such that each bristle has a different geometrical shape at the end and therefore a different bending and wear behavior.

Pulsed extrusion of monofilaments is also known to obtain a monofilament with varying diameter. The monofilament is cut in the region of the constriction to obtain bristles having

tapered ends. Pulsed extrusion cannot be carried out at the large frequencies which would be required for the short bristle lengths of many applications, thereby producing a substantial amount of waste. Moreover, the ends would have irregular shapes.

It is therefore the underlying purpose of the invention to introduce a bristle with tapering bristle end corresponding to GB 2 325 401A which has sufficient bending strength and simultaneously good action of the bristle end. The bristle should furthermore be designed such that it can be produced with reproducible properties.

A bristle of this type is characterized in accordance with the invention in that the soft elastic shaft is additionally surrounded by a jacket made from a plastic which stiffens the shaft.

The inventive bristle has a distinct tapering which permits penetration of the end into narrow gaps, e.g. into the fissures of teeth down to the fissure bottom and permits action on the fissure wall and fissure bottom by elastic deflection. The bristle core thereby provides sufficient bending strength and at the same time good elasticity. The soft, preferably rubber-elastic shaft has similar effects as an eraser due to its higher coefficient of friction. It achieves a more uniform cleaning action since the soft material adjusts well to uneven surfaces.

The degree and length of the tapering are matched such that the bristle end does not deflect, and thereby become ineffective, under small loads. The tapering bristle end is guided by the bristle shaft such that it can penetrate into narrow gaps, e.g. fissures, without premature bending of the bristle itself. The inventive bristle permits very precise application of media, e.g. cosmetics, lip gloss, eye liner etc.

The plastic materials of the core and of the shaft can be mainly selected with regard to their intended function, whereas the bristle jacket provides the required bending strength. When the bristle is bent, the jacket can effect additional cleaning or polishing.

As mentioned above, the shaft is preferably made from a rubber-elastic plastic material, in particular from an elastomer.

In a further preferred embodiment, the shaft and/or jacket extend conically towards the tip of the core, wherein the conical angle defines the bending behavior of the bristle end.

In a further advantageous embodiment, the core also tapers conically such that the conical length defines its bending behavior.

In another variant or in addition to the conical shape, the core can be disposed in the shaft in an axially displaceable fashion to adjust that free length of the core which projects past the shaft to the respective application.

To achieve the same object, the shaft and the jacket may be axially displaceable relative to one another to realize a stepped bristle comprising several components. In both above-mentioned embodiments comprising jacket, shaft and core, their different properties, substantially determined by their materials and geometry, can be effective in the region of the bristle end.

The core can have a round tip to prevent excessive action for short free lengths.

In a preferred embodiment, the core and the jacket are made from a thermoplastic material, whereas the shaft is preferably formed from a thermoplastic elastomer. Suitable thermoplastic materials are polyamides, polyester and also polyethylene or polypropylene.

The above-mentioned plastic materials can be fashioned by extrusion or coextrusion into endless monofilaments from which the bristles are then cut to the desired length.

The conical shape or the length of the conical end can be adjusted to the purpose of use and - for reasons of stability - to the cross-section of the bristle.

The tapering can have a maximum length of 2mm, preferably between 0.1 and 1.00mm, wherein the smallest diameter in the region of the outermost end should be between 0.01 and 0.03mm. At a separation of 0.6mm to approximately 1mm from the bristle tip, the bristle diameter can expand progressively to the conventional size.

In a further advantageous fashion, at least the core is split once or several times in the region of its free end such that the bristle end elastically bends and spreads along the gaps when loaded. This produces an additional action on the walls of ampoule-shaped widenings, in particular of ampoule-shaped fissures which is also supported by the frictional effect of the shaft. Monofilament bristles of similar type which permit a directed spreading are described e.g. in WO 99/24649. In contrast thereto, the inventive bristle is characterized by even thinner "flags" which are evenly packaged through integration into the shaft. The core is substantially produced according to methods described in WO 99/24649.

In accordance with another embodiment, at least the core of the bristle is split once or several times at a separation from its end such that when the bristle end is loaded, only the split region bulges under compression, thereby maintaining its closed end. This, too is a resilient process with corresponding restoring force. The bulge widens the cross-section and the curved bristle sections and edges act on the gaps, in particular of ampoule-shaped fissures.

In a further embodiment, the core can consist of two or more monofilaments whose free ends function as fibers.

In a further embodiment of the invention, the cross-section of the bristle has a material structure which changes from the inside to the outside. It can be realized by coextrusion of different materials or by defined embedding of fillers, e.g. color pigments, in the outer region.

It is thereby recommended to provide the material structure of the core with high elasticity and abrasive resistance and the jacket with a high bending strength. The inventive bristle is preferably produced by coextrusion of core and shaft, and optionally also the jacket, as a multiple component filament. Alternatively, the jacket can be extruded onto a coextruded shaft and core structure.

In a further embodiment, the bristle comprises abrasive means which are embedded at least in the region of the soft shaft to further support the "abrasive" cleaning effect.

Moreover, at least the shaft and the core may have different colors for visualization of their respective effects and to thereby simultaneously provide a kind of wear display, since the tapering core will generally be worn before the soft shaft such that the color of the core will gradually disappear.

The invention also concerns a method for producing bristles having the above-described structure. The multiple component monofilaments obtained by extrusion, larger strand sections of such monofilaments, or bristles cut to length are clamped at a separation from the free end, supported with the core on a circulating grinding surface, and conified through grinding at an inclination with respect to that grinding surface of approximately the cone angle. The applicant describes a technique suitable therefor in EP 0 444 436 A1.

In addition, the bristle can also be supported on the grinding surface at the jacket. This support permits exact conification of the soft rubber-elastic shaft which would otherwise be difficult to grind, and can be very precisely defined by corresponding setting of the cone angle.

Instead or additionally, the core and the shaft can be axially displaced relative to one another until a partial length of the core projects past the shaft. In the same fashion, the jacket and the shaft can be axially displaced relative to one another until a cylindrical partial length of the shaft projects past the jacket.

If the bristle is not conified before axial displacement, it assumes a stepped profile which tapers towards the free end. If conification takes place before, the components forming the bristles merge via inclined surfaces.

The method described by the applicant in EP 0 346 646 A1 is particularly advantageous for such bristle "topography".

The invention also concerns a brush, in particular a tooth brush, comprising a bristle support and a bristle stock mounted thereto having individual bristles or bristles combined into bundles or groups. Such a brush is characterized in that the bristle stock comprises, at least partially, the above-described inventive bristles. These bristles may be optionally disposed only in defined regions of the bristle stock.

In the same manner, the invention can also be used in optionally replaceable tooth brush heads in powered (electrical) tooth brushes in that the bristle stock of such a replaceable tooth brush head is provided with the inventive bristles, optionally, in defined regions only. In particular, a rotary drive produces a particularly good effect in narrow gaps, fissures or the like. Spreading of split bristles is thereby supported by the centrifugal action.

If the bristle stock also comprises other, conventional bristles in addition to the inventive bristles, the latter preferably project past the former to be effective when first applying the brush. The applicant's method according to EP 0 346 646 A1 is recommended for bringing the ends of all bristles of a bristle stock to different levels.

The invention is described below with respect to some embodiments shown in the drawing.

Figs. 1a) to d) each show a schematic representation of the four typical fissure shapes;

Fig. 2 shows a measurement diagram of an ampoule-shaped fissure in accordance with the statistical average;

Fig. 3 shows a measurement diagram of the other three fissure shapes in accordance with the statistical average;

Figs. 4a),b) show a schematic representation of an embodiment of a three-component bristle (Fig. 4a)) and the effects of this bristle (Fig. 4b));

Figs. 5a),b) show another embodiment of the bristle (Fig. 5a)) and the effects of this bristle for another fissure (Fig.5b));

Figs. 6a),b) show another embodiment of the bristle (Fig. 6a)) and the effects of this bristle (Fig. 6b));

Figs. 7a), b) show an embodiment of a two-component bristle (Fig. 7a)) and the effects of this bristle (Fig. 7b));

Figs. 8a), b) show another embodiment of a two-component bristle (Fig. 8a)) and the effects of this bristle (Fig. 8b));

Fig. 9 shows a schematic illustration of the method for conifying the bristle;

Fig. 10 shows an embodiment of a three-component bristle in an enlarged section;

Fig. 11 shows a further embodiment of a two-component bristle in an enlarged partial view; and

Fig. 12 shows an embodiment of a two-component bristle with a core of monofilaments.

The fissure shapes occurring in practice are shown in Fig. 1. Fig. 1a) shows the most critical form with respect to dental hygiene, namely the so-called ampoule shape which initially tapers down like a funnel to the most narrow point and subsequently widens again like a sack. The fissure in accordance with Fig. 1b) is also difficult to reach, the so-called I-shape which has a deep and narrow funnel shape. The V-shape in accordance with Fig. 1c) having funnel walls which

are widely spread is more favorable as is the U-shape in accordance with Fig. 1d) having a U-shaped fissure bottom. The statistical distribution of the series shown in figures 1a) to d) of the different fissure shapes is approximately 7%/11%/21%/61%.

Fig. 2 shows a measurement diagram for ampoule-shaped fissures in accordance with Fig. 1a) which shows the width (abscissa) for a given depth (ordinate). Fig. 3 likewise shows a measurement diagram for the other fissure shapes, wherein the width (abscissa) of 90% of the fissures is greater than or equal to the value given. For ampoule-shaped fissures in accordance with Fig. 2, the width at the most narrow point located at a separation of approximately 0.6mm from the fissure bottom is only approximately 0.01mm. At the same separation from the fissure bottom, the width of the fissures in accordance with Fig. 3 is almost ten times larger.

The following representations show a series of bristles of different bristle end design. Fig. 4a) shows a bristle 1 which is formed e.g. of a three-component filament. It is substantially cylindrical and merges at its useful end 2 via a conically tapering region 3 into a substantially cylindrical tip 4 with a rounded end. It consists of a core 5, forming the tip, e.g. of a polyamide, a shaft 6 of a soft-elastic material, e.g. an elastomer and a reinforcing jacket 7 e.g. of polyamide. The cylindrical region of the bristle 1 has sufficient bending strength for insertion of the bristle

end 2 and in particular the tip 4 e.g. into the fissure in accordance with Fig. 4b). The bristle end 2 penetrates to the bottom 8 of the fissure. When the bristle end 3 meets the fissure bottom 8, it is elastically deflected such that the deeper regions in the fissure 9 are also acted upon and cleaned by the tapering region 2 and the bristle tip 4. At the same time, the shaft 6 rubs against the wall of the fissure 9.

In the embodiment of Fig. 5a), the bristle 1 again consists of a substantially cylindrical filament with a conically tapering end 2. The bristle 1 or its core is slitted once or several times starting from the pointed end 14. This bristle is particularly suited for ampoule-shaped fissures as shown in Fig. 5b). When the bristle 1 penetrates into the fissure 9, it passes the most narrow portion 10 of the fissure 9 in the region of its conical end 2 until it meets the bottom 11. Under small loads, the bristle end 4 spreads open along the slits to form finger-like ends 12 which act on the fissure bottom 11 and the walls of the ampoule-shaped widenings 13. In this case as well, the conical region of the shaft 6 also principally cleans the narrow portion 10. When the pressure is reduced, the elastic restoring force returns the spread ends 12 to their initial position.

Fig. 6a) shows a bristle 1, also with cylindrical jacket 7 and a bristle end 2 which tapers towards a tip 4, wherein the diameter of the core 5 is larger than that of the bristle of Fig. 4 thereby reducing the wall thickness of the shaft 6.

The bristle end 2 is slitted once or several times at its core 5 at a separation from the tip 4 as indicated by the slit 14. When the bristle 1 penetrates the ampoule-shaped fissure 9 and the bristle end 2 meets the fissure bottom 11, the conical section of the bristle end 2 bulges as shown e.g. at 15. This also produces intensive cleaning of the ampoule-shaped fissure, while the larger cross-section of the bristle shaft 6 acts at the most narrow portion 10.

In the embodiment of Fig. 7a) and 8a), the bristle 1 consists of only two components, namely the core 5 and the shaft 6, wherein the core is again made from a stiff plastic material and the jacket 7 from a soft-elastic plastic material. The conically tapering end 2 of the bristle 1 or the core 5, extending in the form of a point, has slits 16 which start at the end and which, in the embodiment shown, are closed when not in use. When the bristle 1 penetrates into a fissure 9, the tapering bristle end 2 passes the narrow point 10 of the ampoule-shaped fissure 9 until it finally meets the bottom 11 of the fissure and the end 4 spreads along the slits 16 to produce finger-like elements 17 which clean, in particular, the fissure bottom (Fig. 7b)).

The embodiment according to Fig. 8a) corresponds substantially to that of Fig. 6a). However, the bristle 1 does not have a jacket 7 as in the embodiment of Fig. 7a). The core 5 tapers in the region of the tapering end and has a gap 18 at a separation from the tip 4. The bristle 1 in

accordance with Fig. 8a) substantially functions in the same way as in Fig. 6b), as is shown in Fig. 8b).

Fig. 9 shows a schematic view of the technique for conifing the bristles in accordance with Figs. 4 through 6. Reference numeral 19 in Fig. 9 designates a grinding surface which rotates about an axis 20. The axis of the bristle 1 which consists of core 5, shaft 6 and jacket 7 is oriented, with respect to the grinding surface 19, at approximately the desired conical angle. The bristle 1 is only initially supported at the jacket and, for increased abrasion, also on the core 5. Since both the jacket 7 and core 5 are made from a stiff material, both these as well as the intermediate shaft 6 of soft-elastic material are properly abraded to thereby produce a precisely conified tip 4.

In the embodiment of Fig. 10, the bristle again comprises a core 5, a shaft 6 and a reinforcing jacket 7 which are coextruded and which can be axially displaced with respect to one another. This can be realized through corresponding selection of the plastic materials used or through sliding means in the bordering layers which are applied during extrusion. The shaft 6 is axially displaced towards the free end 4 with respect to the jacket 7. The core 5 is likewise displaced with respect to the shaft 6, however, by an increased length to produce, in total, a tapering end 2, wherein core 5, shaft 6 and jacket 7 are disposed in a stepped fashion. If the bristle 1 is conified before axial

displacement in accordance with Fig. 10, the steps are eliminated and inclined transition surfaces are produced.

In the embodiment of Fig. 11, the bristle 1 again consists of a core 5, a soft elastic shaft 6 and a reinforcing jacket 7 which contains fillers, e.g. abrasive particles or the like as indicated in the drawing. After cutting, the bristle 1 is initially rounded at its end through grinding or the like. The core 5 is then axially displaced towards the end relative to the shaft 6 and the jacket 7 such that it projects past the shaft 6 and with its rounded free end 21. The shaft 6 is likewise rounded at its free end 22 and the jacket 7 is also rounded at 23.

Fig. 12 shows a bristle 1 with a tapering end 3 which consists of a shaft 26 of a soft-elastic material and a core 24 of several monofilaments 25, wherein the core 24 or the monofilaments 25 also project past the shaft 26 to form the tip 4 of the bristle 1.

Claims

1. Bristle for brushware or brushes, produced by cutting an extruded monofilament to length and being tapered towards their useful ends in a pointed manner and comprising at least two coextruded plastic components with a shaft (6) of a soft elastic plastic material and a core (5) of a harder flexible plastic material, wherein the core (5) projects past the shaft (6) at the useful end (2), thereby forming a tip (4), characterized in that the soft-elastic shaft (6) is surrounded by a jacket (7) of a plastic material which reinforces the shaft (6).
2. Bristle according to claim 1, characterized in that the shaft (6) consists of a rubber-elastic plastic material.
3. Bristle according to claim 1 or 2, characterized in that the shaft (6) consists of an elastomer.
4. Bristle according to any one of the claims 1 through 3, characterized in that the shaft (6) and/or the jacket (7) extend conically towards the tip (4) of the core (5).
5. Bristle according to any one of the claims 1 through 4, characterized in that the core (5) has a conical tip.
6. Bristle according to any one of the claims 1 through 5, characterized in that the core (5) and the shaft (6) can be axially displaced relative to one another.

7. Bristle according to any one of the claims 1 through 6, characterized in that the shaft (6) and the jacket (7) can be axially displaced relative to one another.
8. Bristle according to any one of the claims 1 through 7, characterized in that the core (6) is rounded at its tip (20).
9. Bristle according to any one of the claims 1 through 8, characterized in that the core (5) consists of a thermoplastic material, polyamide or polyester and the shaft (6) consists of a thermoplastic elastomer.
10. Bristle according to any one of the claims 1 through 9, characterized in that the jacket (7) consists of a thermoplastic material, polyamide or polyester.
11. Bristle according to claim 9 or 10, characterized in that the thermoplastic material is polyamide, polyethylene, polypropylene or polyester.
12. Bristle according to any one of the claims 1 through 11, characterized in that the bristle (1) extends conically on a partial length of up to 2mm.
13. Bristle according to any one of the claims 1 through 12, characterized in that the bristle (1) extends conically on a partial length of between 0.1 and 1mm.

14. Bristle according to any one of the claims 1 through 12, characterized in that the diameter of the core (5) at the pointed end (4) is between 0.01 and 0.03mm.
15. Bristle according to any one of the claims 1 through 14, characterized in that at least the core (5) can be split once or several times in the region of its exposed end (4) and be spread beginning at its end.
16. Bristle according to any one of the claims 1 through 14, characterized in that at least the core (5) is split once or several times in the region of its exposed end (4) and at a separation therefrom, wherein the split region bulges elastically when pressure is exerted on the end.
17. Bristle according to any one of the claims 1 through 16, characterized in that the core (27) consists of two or more thin monofilaments (25).
18. Bristle according to any one of the claims 1 through 17, characterized in that the cross-section of its material structure changes from the inside to the outside.
19. Bristle according to any one of the claims 1 through 18, characterized in that its core (5) has a material structure of high elasticity and abrasion resistance and its jacket (7) has a high bending strength.

20. Bristle according to any one of the claims 1 through 19, characterized in that it is produced through coextrusion of shaft (6), core (5) and optionally jacket (7).
21. Bristle according to any one of the claims 1 through 19, characterized in that it is produced through extrusion of the jacket (7) onto the shaft (6) with coextruded core (5).
22. Bristle according to any one of the claims 1 through 21, characterized in that it comprises abrasive means which are embedded at least in the region of the soft shaft (6).
23. Bristle according to any one of the claims 1 through 22, characterized in that at least the shaft (6) and the core (5) have different colors.
24. Method for producing bristles according to any one of the claims 1 through 23, characterized in that the bristle (1) or a monofilament forming same or a section of such a monofilament is conified through grinding by clamping it at a separation from the free end, supported with the core on a circulating grinding surface (19), and set at an inclination with respect to that circulating grinding surface (19) corresponding substantially to the cone angle.

25. Method according to claim 24, characterized in that the bristle, including core (6) and jacket (7), is supported on the grinding surface (19).
26. Method for producing bristles according to any one of the claims 1 through 6, characterized in that the core (5) and the shaft (6) are axially displaced relative to one another until part of the length of the core (5) projects past the shaft (16).
27. Method for producing a bristle according to any one of the claims 1 through 7, characterized in that the jacket (7) and the shaft (5) are axially displaced relative to one another until a cylindrical partial length of the shaft projects past the jacket.
28. Method according to any one of the claims 24 through 27 for producing bristles with stepped core (5) and shaft (6) and/or jacket (7), wherein part of the length of at least the shaft (6) and/or the jacket (7) are conical.
29. Brush, in particular tooth brush comprising a bristle support and a bristle stock mounted thereto, of individual bristles or bristles combined into bundles or groups, characterized in that the bristle stock at least partially comprises bristles (1) according to any one of the claims 1 through 23.

30. Brush according to claim 29, characterized in that the bristles (1) according to any one of the claims 1 through 23 are disposed only in defined regions of the bristle stock.
31. Brush, in particular tooth brush head for driven tooth brushes comprising a brush support and a brush stock mounted thereto which is made of individual bristles or of bristles combined into bundles or groups, characterized in that the bristle stock at least partially comprises bristles (1) according to any one of the claims 1 through 23.
32. Brush according to claim 31, characterized in that the bristles (1) according to any one of the claims 1 through 23 are only disposed in defined regions of the bristle stock.
33. Brush according to claim 29 or 30, characterized in that the bristles (1) according to any one of the claims 1 through 23 project past the other bristles of the bristle stock.



Fig. 1 (a) (b) (c) (d)




Fig. 2

Fig. 3




Fig. 6a

Fig. 5a

Fig. 4a




Fig. 6b




Fig. 5b




Fig. 4b




Fig. 7a




Fig. 7b




Fig. 8a




Fig. 8b




Fig. 9




Fig. 10




Fig. 11




Fig. 12

COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY

(Includes Reference to PCT International Applications)

ATTORNEY DOCKET NUMBER

18980.0

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Bristle, Method for producing a bristle and brushware
comprising such bristles

the specification of which (check only one item below):

☐ is attached hereto.

☐ was filed as United States application

Serial No. _____

on _____

and was amended

on _____ (if applicable)

☒ was filed as PCT international application

Number PCT/EP00/06688

on July 13, 2000

and was amended under PCT Article 19

on _____ (if applicable)

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is known to me or other person(s) involved in the preparation or prosecution of this application to be material to the examination of this application and to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I hereby authorize the U.S. attorney or agent named herein to accept and follow instructions from _____

as to any action taken in the Patent and Trademark Office regarding this application without direct communication between the U.S. attorney or agent and the undersigned. In the event of a change in the persons from whom instructions may be taken, the U.S. attorney or agent named herein will be so notified by the undersigned.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

PRIOR FOREIGN/PCT APPLICATION(S) AND ANY PRIORITY CLAIMS UNDER 35 U.S.C. 119				
COUNTRY (If PCT, indicate "PCT")	APPLICATION NUMBER	DATE OF FILING (day, month, year)	PRIORITY CLAIMED UNDER 35 USC 119	
Germany /	199 32 376.3 ✓	13. July 1999 /	<input checked="" type="checkbox"/> YES	<input type="checkbox"/> NO
			<input type="checkbox"/> YES	<input type="checkbox"/> NO
			<input type="checkbox"/> YES	<input type="checkbox"/> NO
			<input type="checkbox"/> YES	<input type="checkbox"/> NO
			<input type="checkbox"/> YES	<input type="checkbox"/> NO

Combined Declaration For Patent Application and Power of Attorney (Continued) (Includes Reference to PCT International Applications)		ATTORNEY DOCKET NUMBER 18980.0		
I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) or PCT international application(s) designating the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in that/those prior application(s) in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing date of the prior application(s) and the national or PCT international filing date of this application:				
PRIOR U.S APPLICATIONS OR PCT INTERNATIONAL APPLICATIONS DESIGNATING THE U.S. BENEFIT UNDER 35 U.S.C. 120				
U.S. APPLICATIONS		STATUS (Check one)		
U.S. APPLICATION NUMBER	U.S. FILING DATE	PATENTED	PENDING ABANDONED	
PCT APPLICATIONS DESIGNATING THE U.S.				
PCT APPLICATION NUMBER	PCT FILING DATE	U.S. SERIAL NUMBERS ASSIGNED (if any)		
POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith (List name and registration number)				
Paul J. Vincent Reg. No. 37,461				
Send Correspondence to:		Telephone 49-721-943 28 15 Fax 49-721-943 28 40 + 943 28 50		
Licht, Lempert, & Lasch Bergwaldstr. 1 D-76227 Karlsruhe, Germany				
201	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	POST OFFICE ADDRESS	CITY	STATE & ZIP CODE/COUNTRY
202	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	POST OFFICE ADDRESS	CITY	STATE & ZIP CODE/COUNTRY
203	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	POST OFFICE ADDRESS	CITY	STATE & ZIP CODE/COUNTRY
I hereby declare under penalty of perjury under the laws of the United States of America that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine and imprisonment, or both, under section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon				
SIGNATURE OF INVENTOR 201		SIGNATURE OF INVENTOR 202		SIGNATURE OF INVENTOR 203
DATE		DATE		DATE
Dec. 17, 2001				